

Technical data sheet in accordance with ASTM

Material

NBR NB707101

black

cross linking: sulfur

revision index

3

revision date

5/2/2018

page

1 / 3

Physical properties

	nominal range	typical values	
Density ASTM D 1817	1.23 ±0.02	1.23	g/cm ³
Hardness ASTM D2240, Shore A	70 ±5	67	Shore
Tensile strength ASTM D412	---	17.5	MPa
Elongation at Break ASTM D412	---	325	%
Low temperature test ASTM D1329, TR10	---	-27.1	°C
Low-temperature resistance ASTM D 2137, 3 min, pass	---	-35	°C
Compression set ASTM D395, B, 22 h, 100 °C, 25 %	---	8	%

Declarations of conformity

	Country	Part	Remark	Expires	unlimited
ADI Free					☒
RoHS			Restricted substances in electrical and electronic equipment		☒

Change after aging

in Air: 70h/100°C

		Typ. values		
		Base value	After aging	difference
Hardness (ASTM D2240, Shore A)	Shore	67	71	4
Tensile strength (ASTM D412)	MPa	17.5	17.1	-2 %
Elongation at Break (ASTM D412)	%	325	276	-15 %
volume change (ASTM D471)	%		-0.4	

Freudenberg

 Dichtomatik Vertriebsgesellschaft für Technische Dichtungen mbH
 Global Material Technology
 Viviane Rellstab

 Telefon: +49 40 66989 316
 Fax: +49 40 66989 9316
 Email: Viviane.Rellstab@dichtomatik.de


Technical data sheet in accordance with ASTM

Material

NBR NB707101

black

cross linking: sulfur

revision index

3

revision date

5/2/2018

page 2 / 3

Change after aging in ASTM-Oil No. 1: 70h/100°C

Hardness (ASTM D2240, Shore A)
Tensile strength (ASTM D412)
Elongation at Break (ASTM D412)
volume change (ASTM D471)

Shore
MPa
%
%

Typ. values			
Base value	After aging	difference	
67	76	9	
17.5	17.9	2 %	
325	279	-14 %	
	-9.5		

Change after aging in ASTM-Oil No. 3: 70h/100°C

Hardness (ASTM D2240, Shore A)
Tensile strength (ASTM D412)
Elongation at Break (ASTM D412)
volume change (ASTM D471)

Shore
MPa
%
%

Typ. values			
Base value	After aging	difference	
67	70	3	
17.5	17.7	1 %	
325	286	-12 %	
	1.6		

Freudenberg

Dichtomatik Vertriebsgesellschaft für Technische Dichtungen mbH
Global Material Technology
Viviane Rellstab

Telefon: +49 40 66989 316
Fax: +49 40 66989 9316
Email: Viviane.Rellstab@dichtomatik.de



Technical data sheet in accordance with ASTM

Material **NBR NB707101**

black

cross linking: sulfur

revision index

3

revision date

5/2/2018

page 3 / 3

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Dichtomatik Vertriebsgesellschaft für Technische Dichtungen mbH
Global Material Technology
Viviane Rellstab

Telefon: +49 40 66989 316
Fax: +49 40 66989 9316
Email: Viviane.Rellstab@dichtomatik.de

